WTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

SIGNATURE FLOORCOVERINGS CLIENT :

PTY LTD

13 WURUNDJERI DRIVE EPPING VIC 3076

TEST NUMBER : 7-561350-JV DATE

: 04/08/2008

SAMPLE DESCRIPTION Clients Ref: Friendly Tiles - Chakra

Cut and loop pile carpet tile

Colour: charcoal

Approx. pile height: 4 to 6 mm

Material Specification:

Nominal composition: 100% solution dyed nylon

Nominal total pile mass: 1030g/m2 Nominal backing: thermoplastic

ASISO 9239.1-2003

Reaction to Fire Tests for Floorings

Part 1

Determination of the Burning Behaviour

using a Radiant Heat Source

Date of sample arrival:

Date tested:

10.07.2008 01.08.2008

Results:

CHF (Critical Heat Flux / Critical Radiant Flux) ેર

Mean

141

1

Length Width

9.6 9.8 9.8 9.7 kW/m210.1 kW/m2

Smoke Value

Length Width

148 124 142

132

% min 4 min

Observations: melting, blistering, penetration of flame through to

substrate

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

169553

1

(c) Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for Chemical Testing of Textiles & Related Products Accreditation No. Mechanical Testing of Textiles & Related Products

- Heat & Temperature Measurement

983 Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

