AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Signature Floorcoverings Pty Ltd

> 13 Wurundjeri Drive Epping VIC 3076

19-001502 Test Number :

112454

Issue Date 14/06/2019 **Print Date** 14/06/2019

Order Number:

"Rhythm- Comfibak" **Sample Description** Clients Ref:

> Multi Level Loop Pile Carpet Tile Black with grey Colour: End Use: Flooring

Solution Dyed Nylon Nominal Composition:

Nominal Mass per Unit Area/Density: Approx: 5.9kg/m2

Nominal Thickness: 7mm

AS/ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a

Radiant Heat Source

Date of Sample Arrival 21/03/2019 **Date Tested** 13/06/2019

CHF Value 2 1 3 Mean Length 6.7 6.3 6.9 6.6 kW/m² Width 67 kW/m² Smoke Value 2 1 3 Mean Length 261 227 222 237 %.min Width 254 %.min

Melting Yes Penetration of flame through to substrate Yes

169322 34909 Page 1 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No Accreditation No

983

· Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.





A. JACKSON B.Sc.(Hons)

AWTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: Signature Floorcoverings Pty Ltd

> 13 Wurundjeri Drive Epping VIC 3076

19-001502 Test Number :

Issue Date 14/06/2019 **Print Date** 14/06/2019 Order Number: 112454

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

169322 34909 Page 2 of 2

Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing

Mechanical Testing

Performance & Approvals Testing

: Accreditation No Accreditation No

· Accreditation No. 1356

983

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A. JACKSON B.Sc.(Hons)