

Attn: Mr Damien Ryan, Technical Manager  
m/s SIGNATURE FLOORCOVERINGS PTY LTD  
13 Wurundjeri Drive Epping Vic 3076

LABORATORY TEST REPORT  
**P172163**

## RIGID 7.0 mm

Sample description as provided by customer

Order No. PO109169

Overall Thickness 7.0mm Wear Layer 0.55mm Plank Thickness 5.5mm Backing EVA Thickness 1.5mm  
Dimensions 900 mm x 225 mm

TEST METHOD: AS.ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by the Building Code of Australia (BCA) and National Construction Code 2015 (NCC) specifications C1.10. Sample conditioning as specified in BS EN 13238.2010.

Sample Submitted Date Jun 2017

Test Date 22 Jun 2017

Total Thickness mm

### Assembly System: DIRECT STICK (Details Below).

The floor covering was directly stuck to the substrate using Vinyl adhesive.

**Substrate: Non-Combustible** - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.  
The Holding Torque on Specimen Frame was 2Nm.

The standard requires two Initial Tests be conducted on samples mounted in both Length and Width directions. Two further samples are then tested in whichever direction has the lowest Critical Radiant Flux.

Initial Tests: Length Direction Critical Radiant Flux **12.2 kW/m<sup>2</sup>**  
Width Direction Critical Radiant Flux **12.2 kW/m<sup>2</sup>**

	Specimen Tests conducted in the Length Direction			
	Specimen #1	Specimen #2	Specimen #3	Mean
Critical Radiant Flux (kW/m <sup>2</sup> )	12.2	12.2	12.2	12.2
Smoke Development Rate (%.min)	104	106	92	101

The values quoted below are as required by BCA and NCC Specification C1.10 Fire Hazard Properties (Floors).  
The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

**Mean Critical Radiant Flux **12.2** kW/m<sup>2</sup>**

**Mean Smoke Development Rate **101** %.min**

Observations: The samples shrunk away from the heat source, ignited and burnt a very short distance.

AS.ISO 9239.1 Clause 9(o) The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

All information required for compliance with the BCA and NCC is given on this test report page.

Page 1 of 2

(v5-0, 11/03/2017)



ACCREDITED FOR  
TECHNICAL  
COMPETENCE

M. B. Webb  
Technical Manager

DATE: 22 Jun 2017

Performance & Approvals  
Accreditation No. 15393  
Accredited for compliance with ISO/IEC 17025.

**TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS**

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	269	275	/															
2	256	/																
3	246	/																

**TESTS**

**BURNING CHARACTERISTICS**

**SMOKE PRODUCTION**

Specimen	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)	Maximum Light Attenuation (%)	Smoke Development Rate (%.min)
Initial Test: Width	50	743	19	98
Specimen Tests: Length				
1	50	769	21	104
2	50	761	22	106
3	50	727	21	92
Mean	50	752	21	101



ACCREDITED FOR  
**TECHNICAL  
COMPETENCE**

**M. B. Webb**  
Technical Manager

DATE: 22 Jun 2017

Performance and Approvals  
Accreditation No. 15393  
Accredited for compliance  
with ISO/IEC 17025.

2004 04 09 1046 22 June 2017